

MaxProof® 405

Liquid waterproofing admixture

Description

MaxProof 405 is a liquid, chloride free waterproofing admixture for concrete and cement-based mortars. It effectively blocks the pores in the concrete and the mortars. So, it stops water absorption and prevents the passage of water and moisture. **MaxProof 405** provides permanent waterproofing for the hardened concrete.

Features and benefits

- Does not rely on film formation. It becomes a permanent part of the concrete/mortar and will not deteriorate or evaporate.
- Fast dispersing during mixing with good distribution throughout the mix.
- Chloride free. Does not corrode steel reinforcement.
- Breathable.

Recommended for

MaxProof 405 is used to waterproof concrete and cement-based mortars in many areas such as:

- Basements and foundations.
- Potable water and waste water treatment plants.
- Swimming pools and water tanks.
- Facades, external walls.
- Wet areas such as showers, bathrooms, toilets, kitchens, balconies and roofs.

Composition

MaxProof 405 contains a blend of waterproofing ingredients. It does not contain chlorides or nitrates.

Packaging

MaxProof 405 is available in 5 & 20 kg jerrycans.

Coverage

MaxProof 405 is used at the rate of 3% - 5% of cement content.

Technical data

Density	1.05 kg/liter
Appearance	Viscous yellow liquid

Mixing

Dilute one part of **MaxProof 405** with 6-10 parts (by volume) of clean water, in a clean container, and stir well. This is best carried out by first mixing 1 part of **MaxProof 405** with 1 part of clean water and then adding the remaining water.

Application

Concrete surfaces must be mechanically roughened. Cracks, porous areas and damaged concrete should be cut out and made good using suitable repair mortar. Water leakage, if any, should be stopped prior to applying waterproofing mortar modified with **MaxProof 405**.

When **MaxProof 405** will be used to produce waterproof mortar, mix sand/cement mortar to a trowelable consistency. Apply it using steel trowel at maximum application thickness of 6 mm. In case that two coats should be applied, the second coat is best applied when the first coat has begun to stiffen (usually 4-5 hours). Then, apply a thrown coat render. It should be rough enough to bond the following cement-based plaster.

For best results, cement should be fresh Portland cement. Sand should be sharp, clean and graded 0 - 3 mm. Soft and rounded sands are unsuitable.

Curing

Good curing is essential. Always cure with tap water. Keep damp for 5 days. Cover the work with wet hessian covered with polyethylene sheet.

Important notes

Waterproofing properties may be affected by concrete mix design (the use of dusty sand or poorly graded sand, type of Portland cement,

cement content and w:c ratio), placing, vibrating & finishing techniques and adequate curing.

Storage and shelf life

If stored unopened in a dry place at a temperature between +5°C and +30°C away from sources of heat and moisture, shelf life is 12 months from the date of manufacture printed on the pack.

Health and Safety

When it comes in contact with sweat or other body fluids causes irritant alkaline reaction and allergic reactions to those predisposed. It can cause damage to eyes. In case of contact with eyes or skin wash immediately with plenty of water and seek medical attention. Dispose excess material to special waste collection point in accordance with local & national regulation. Keep out of reach of children.

For further information, please ask for Safety Data Sheet for this product.

The most up-to-date TDS can be obtained from ACC Customer Service Department, or downloaded from our website: www.acc.com.eg.

More from ACC

A wide range of construction chemicals, specialty mortars and specialized building materials are manufactured by ACC which include:

- Waterproofing.
- Flooring.
- Tile Adhesives & Grouts.
- Concrete Repair.
- Non-Shrink Grouts.
- Bonding Agents.
- Exterior Façade Coatings.
- Premixed Fairing Coats, Renders & Mortars.
- Putties (stucco).
- Sealers & Emulsion Paints.